Thesis Provides Initial Metallurgical Results from Ranch Project With Up to 98% Gold Recovery and Additional Copper and Silver By-Product Credits

12.10.2022 | Newsfile

Vancouver, October 12, 2022 - Thesis Gold Inc. (TSXV: TAU) (WKN: A2QQ0Y) (OTCQX: THSGF) ("Thesis" or the "Company") is pleased to announce the initial metallurgical results performed on their 100% owned Ranch Project. The Ranch property is located in the Golden Horseshoe of north-central British Columbia (BC), Canada. The metallurgical test work showed that all samples responded well, achieving between 90% to 98% gold recovery (Table 3).

Dr. Ewan Webster, President and CEO of Thesis stated, "We are very pleased by these initial metallurgical results. All the mineralized zones demonstrate the ability to produce high-quality concentrates from simple, low-cost conventional extraction methods. This milestone represents an important step in reducing the overall risk of the project as we advance towards a future resource, engineering, and economic studies."

Metallurgical Program Details

Composite core samples from the Bonanza, Ridge, Thesis II, and Thesis III Zones at Ranch were analyzed. Sample selection was based on geological considerations, core logging, and geochemical data to best represent a conceptual resource. Core samples were shipped for metallurgical testing to Bureau Veritas Minerals (BV) Metallurgical Division, an accredited global laboratory facility located in Richmond, BC. BV composited the core samples and undertook the related analytical and bench scale test work. The study was directed and supervised by F. Wright Consulting Inc., with Mr. Frank Wright, P.Eng., acting as the Qualified Person (QP) as defined by NI43-101. Mr. Wright has had extensive process development experience focusing on precious metal projects in northern BC.

Table 1: Metallurgical Composite Location and Description

Date Line

Met Comp. ID (DH depth m)	Zone	Drill Hole (DH) Number	Geo ID from	Geo ID to	Description
BN3 (12-30)	Bonanza	21BNZDD03	B0015105.	125	Higher S, Shallow potential oxidation & cyanicide, sig Cu
BN3 (30-35)	Bonanza	21BNZDD03	B00151268	khellip;13	1 Lower S, but with elevated Au
BN7 (34-42)	Bonanza	21BNZDD07	B00153838	khellip;39	3 Higher Au, Cu Intervals with 1-3%S
BN7 (42-46)	Bonanza	21BNZDD07	B00153948	khellip;39	7 Lower Gold Copper Intervals, ~1%S
RZ9 (131-143)	Ridge	21RDGDD009	B00191898	khellip;20	2 deeper with moderate Cu (~0.2%), high Ag, 5-10% S
RZ9 (143-153)	Ridge	21RDGDD009	B0019203 8	khellip;21	3 deeper with elevated Cu+Ag
RZ9 (153-158)	Ridge	21RDGDD009	B00192148	khellip;22	1 deeper with lower Cu @~500 ppm possible cyanicide iss
RZ12 (36-40)	Ridge	21RDGDD012	2B00073238	khellip;32	6~1% sulphur, potentially oxidized
RZ12 (40-49)	Ridge	21RDGDD012	B00073278	khellip;33	8 very low sulphur, low (<100 ppm) potentially oxide Cu, m
RZ12 (52-58)	Ridge	21RDGDD012	2B00073438	khellip;34	8 RZ12 (52-58) very low sulphur, similar to #9
MZ7 (23-41)	Thesis 3	21TH3DD007	B00108248	khellip;84	5 Main Zone upper intercept, <200 ppm Cu, ~4% S (Thesis
MZ8 (105-111)	Thesis 2	21TH2DD008	B00083128	khellip;31	8 Main Zone elevated Cu (Thesis 2)
MZ8 (111-131)	Thesis 2	21TH2DD008	B00083198	khellip;34	6 Main Zone, <200 ppm Cu, ~3-4%S (Thesis 2)
LW8 (163-189)	Thesis 2	21TH2DD008	B00083688	khellip;40	1 Lower West Zone Thesis 2, <200 ppm Cu, 1-4% S

Abbreviations: Met Comp - Metallurgical Composite, m - metres, sig - significant, S - Sulphur, Cu - Copper, Au -Gold, Ag - Silver.

At BV, the individual core samples were blended into 14 composites comprised from contiguous core interval

05.11.2025 Seite 1/4

splits of 4 m to 26 m in length. These composites represent various mineralogy and spatial areas from specific depth and zones within the potential future resource areas. Composite identification (Met Comp. ID) relating to zone of origin, drill hole number, and depth are provided in Table 1.

The corresponding head analyses for principal metals of interest, as well as sulfur speciation, is provided in Table 2.

Table 2: Metallurgical Composite Head Assays

Composite	Assayed Head Analyses					
Sample	Gold (Au)	Silver (Ag) ⁽	Copper (Cu) (tot)	Sulphur (S) (tot)) S	
ID	g/t	g/t	%	%	%	
BN3 (12-30)	10.9	3.2	0.04	6.92	6.41	
BN3 (30-35)	9.85	0.7	0.01	1.27	0.44	
BN7 (34-42)	39.7	4.9	0.89	4.06	3.29	
BN7 (42-46)	0.97	0.6	< 0.01	1.12	0.94	
RZ9 (131-143)	0.83	179	0.17	6.45	5.79	
RZ9 (143-153)	13.1	177	0.9	12.7	11.9	
RZ9 (153-158)	1.96	29	0.05	3.03	2.91	
RZ12 (36-40)	2.62	47	< 0.01	0.93	0.92	
RZ12 (40-49)	2.29	24	< 0.01	0.08	0.06	
RZ12 (52-58)	1.11	18	< 0.01	0.06	< 0.05	
MZ7 (23-41)	2.01	1.1	< 0.01	4.05	3.64	
MZ8 (105-111)	1.4	2.2	0.17	3.71	3.64	
MZ8 (111-131)	1.19	0.8	< 0.01	3.36	3.27	
LW8 (163-189)	1.27	0.7	<0.01	2.62	2.44	

Note: Au is average of two fire assays. Ag is by fire assay >50 ppm, or by ICP if <50 ppm. Abbreviation: g/t - grams per tonne.

Discussion of Results

Duplicate fire assays provided average gold (Au) grades that ranged from 0.83 grams per tonne (g/t) to 39.7 g/t for the composites. Silver (Ag) content was close to 180 g/t in two of the composite samples and was more strongly associated with copper, although not necessarily in strong correlation. Silver grades were otherwise less than 50 g/t, or in half the composites at less than 5 g/t.

Appreciable copper (Cu) was detected in three of the composites at 0.17%, 0.89% and 0.90%, with only minor oxidized copper (Cuox) present. Organic carbon was typically at or below the 0.02% detection limit. As noted in the mineralogical examination, most of the total sulphur (Stot) was present as pyrite, with some sulphide oxidation present to a varying degree as indicated by the sulphide sulphur (S--) analyses as compared to total sulphur.

Due to the changes in grade and mineralogy, there is variability in the process response. Gravity pre-treatment does not appear to benefit most of the composites, although it is justified for higher grade feeds, recovering up to half of the contained gold. A significant consideration in process selection is the sulfur content and extent of sulphide oxidation. Leaching was shown to be best suited to oxidized and lower S material, with flotation showing a better response to composites containing >1% sulphide sulphur. Gold recovery for the sulphide feeds is provided in Table 3, below.

Table 3: Open Cycle Flotation Response

	# of	G	old Grade (g/t	% Bulk Au	
Comp. ID	Cleaning	Calc.	Cleaner Conc	Tailing	Poorus *
	Stages	Head	Cleaner Conc	. railing	Recovery
RZ9 (153-158)	1	2.05	18.1	0.25	90
MZ8 (111-131)	1	1.08	7.3	0.09	93.7
BN7 (42-46)	1	0.9	18	0.05	95.3

05.11.2025 Seite 2/4

BN3 (30-35)	3	12.2	893	0.18	98.7
LW8 (163-189)	3	1.22	15.7	0.07	95.2
MZ8 (105-111)	3	1.27	9.8	0.09	94.8
BN3 (12-30)	3	13.9	93	0.2	98.9
RZ9 (131-143)	3	0.96	6.4	0.03	97.4
MZ7 (23-41)	3	2.29	22.2	0.07	97.8
RZ12(36-40)	2	2.51	53	0.25	91.9

^{*} includes rougher & Ro. Scav conc.

The results in Table 3 were not fully optimized during this preliminary testing program. However, the work to date indicates a moderate grind with a particle size of approximately 80% passing (P80) of 74 microns or coarser is sufficient for the float feed. Cleaning should be done in approximately 3 stages and final grade will be dependent on Au:S ratio in the feed. For the composites tested, the cleaned concentrate grade ranged from 6 g/t to over 800 g/t Au. Bulk tailing grades were less than 0.25 g/t Au, and often less than 0.10 g/t Au. This resulted in a final bulk float recovery that ranged between 90% to 98%, with recoveries during cleaning holding up well in open cycle testing. The grade recovery relationship can be better established with further optimization and locked cycle testing, planned for the next phase of test work.

Samples with elevated copper and silver responded well to differential flotation. The primary float product produced a cleaned concentrate grade exceeding 22% Cu, with additional gold and silver credits. Copper recovery will be dependent on head grade and ratio to pyrite. Most of the remaining precious metal can be recovered into a secondary concentrate resulting in an overall recovery of 97% for both gold and silver. Samples with lower sulphide content (<1% S--) responded better to whole rock leaching than to flotation. The results using 48-hour leach retention time provided for 95% gold recovery.

The composites studied had significant variability in grade and mineralogy but provided gold recoveries consistently exceeding 90%. Additional testing for advancement of the treatment flowsheet is warranted in conjunction with exploration. In summary, the Ranch Project showed an excellent initial response to conventional mineral processing procedures and supports proceeding toward a preliminary economic evaluation.

The technical content of this news release has been reviewed and approved by Michael Dufresne, M.Sc, P.Geol., P.Geo., and Mr. Frank Wright, P.Eng., qualified persons as defined by National Instrument 43-101.

On behalf of the Board of Directors Thesis Gold Inc.

"Ewan Webster"

Ewan Webster Ph.D., P.Geo. President, CEO, and Director

About Thesis Gold Inc.

Thesis Gold is a mineral exploration company focused on proving and developing the resource potential of the 17,832-hectare Ranch Gold Project located in the "Golden Horseshoe" area of northern British Columbia, approximately 300 km north of Smithers, B.C. For further details about the Ranch Gold Project and the 2022 drill program, please click here to watch videos on the project.

For further information or investor relations inquiries, please contact:

Dave Burwell
Vice President
The Howard Group Inc.

Email: dave@howardgroupinc.com

Tel: 403-410-7907

05.11.2025 Seite 3/4

Toll Free: 1-888-221-0915

Nick Stajduhar Director Thesis Gold

Email: nicks@thesisgold.com

Neither the TSX Venture Exchange nor its Regulation Services Provider (as that term is defined in the policies of the TSX Venture Exchange) accepts responsibility for the adequacy or accuracy of this press release.

Cautionary Statement Regarding Forward-Looking Information

This press release contains "forward-looking information" within the meaning of applicable Canadian securities legislation. Forward-looking information includes, without limitation, statements regarding the use of proceeds from the Company's recently completed financings and the future plans or prospects of the Company. Generally, forward-looking information can be identified by the use of forward-looking terminology such as "plans", "expects" or "does not expect", "is expected", "budget", "scheduled", "estimates", "forecasts", "intends", "anticipates" or "does not anticipate", or "believes", or variations of such words and phrases or state that certain actions, events or results "may", "could", "would", "might" or "will be taken", occur" or "be achieved". Forward-looking statements are necessarily based upon a number of assumptions that, while considered reasonable by management, are inherently subject to business, market, and economic risks, uncertainties, and contingencies that may cause actual results, performance, or achievements to be materially different from those expressed or implied by forward-looking statements. Although the Company has attempted to identify important factors that could cause actual results to differ materially from those contained in forward-looking information, there may be other factors that cause results not to be as anticipated, estimated, or intended. There can be no assurance that such information will prove to be accurate, as actual results and future events could differ materially from those anticipated in such statements. Accordingly, readers should not place undue reliance on forward-looking information. Other factors which could materially affect such forward-looking information are described in the risk factors in the Company's most recent annual management's discussion and analysis, which is available on the Company's profile on SEDAR at www.sedar.com. The Company does not undertake to update any forward-looking information, except in accordance with applicable securities laws.

To view the source version of this press release, please visit https://www.newsfilecorp.com/release/140154

Dieser Artikel stammt von Rohstoff-Welt.de Die URL für diesen Artikel lautet:

 $\underline{https://www.rohstoff-welt.de/news/425337--Thesis-Provides-Initial-Metallurgical-Results-from-Ranch-Project-With-Up-to-98 Prozent-Gold-Recovery-and-Additional Control of the State of t$

Für den Inhalt des Beitrages ist allein der Autor verantwortlich bzw. die aufgeführte Quelle. Bild- oder Filmrechte liegen beim Autor/Quelle bzw. bei der vom ihm benannten Quelle. Bei Übersetzungen können Fehler nicht ausgeschlossen werden. Der vertretene Standpunkt eines Autors spiegelt generell nicht die Meinung des Webseiten-Betreibers wieder. Mittels der Veröffentlichung will dieser lediglich ein pluralistisches Meinungsbild darstellen. Direkte oder indirekte Aussagen in einem Beitrag stellen keinerlei Aufforderung zum Kauf-/Verkauf von Wertpapieren dar. Wir wehren uns gegen jede Form von Hass, Diskriminierung und Verletzung der Menschenwürde. Beachten Sie bitte auch unsere AGB/Disclaimer!

Die Reproduktion, Modifikation oder Verwendung der Inhalte ganz oder teilweise ohne schriftliche Genehmigung ist untersagt! Alle Angaben ohne Gewähr! Copyright © by Rohstoff-Welt.de -1999-2025. Es gelten unsere AGB und Datenschutzrichtlinen.

05.11.2025 Seite 4/4