

Independence Gold Reports Metallurgy Results from the 3Ts Project, BC

10.09.2025 | [Newsfile](#)

Vancouver, September 10, 2025 - [Independence Gold Corp.](#) (TSXV: IGO) (OTCQB: IEGCF) (the "Company" or "Independence") is pleased to announce updated metallurgical recovery results from the 3Ts Project. Located approximately 185 kilometres southwest of Prince George, British Columbia, the 3Ts Project comprises thirty-one mineral claims covering approximately 35,486 hectares in the Nechako Plateau region. The project is situated 16 km southwest of [Artemis Gold Inc.](#)'s Blackwater Mine and covers a low-sulphidation epithermal quartz-carbonate vein district within which at least nineteen known mineralized veins, ranging from 50 to over 1,100 metres in strike length and true widths of up to 32 m have been identified.

Metallurgical testing was conducted by Base Metallurgical Laboratories Ltd. in Kamloops, BC., and returned positive results that further confirmed previous metallurgical testing. These tests evaluated a three-stage process including gravity concentration, flotation, and cyanide leaching.

Sample Selection and Preparation

Composite samples comprised of mineralized vein material were collected from drill core recovered during the 2024 to 2025 program and were selected to test mineralized veins at depth as well as two new veins (Johnny and Larry) that were intersected during the recent drill program. The three tests were:

- Tommy Vein "Deep"
 - 3TS-24-27 from 361.39m to 429.96m*, including grades up to 13.46 g/t gold and 119.0 g/t silver (see news release dated January 20, 2025)
- Johnny Vein System
 - 3TS-25-05 from 13.59m to 85.50m*, including grades up to 19.95 g/t gold and 176.0 g/t silver (see news release dated March 20, 2025)
- Larry Vein
 - 3TS-27-07 from 179.00m to 198.40m*, including grades up to 20.36 g/t gold and 333 g/t silver (see news release dated March 26, 2025)

(* mineralized samples selected from interval rather than a complete run through these lengths)

Gravity, Floatation and Leaching Test Results

Composite samples were subjected to three testing stages; gravity, gravity and floatation, and gravity, floatation and cyanide leaching (see below for methodology and detailed results for each stage). On average across the three composites, the full flowsheet yields program-level averages of roughly 92% gold and 90% silver.

These results are consistent with, and in some cases approach or exceed, historical recoveries reported in 2021, which included 93.9% gold and 92.4% silver recovery for the Tommy Vein, and up to 97.9% gold and 95.5% silver recovery for the Ted-Mint Vein (see news release dated March 4, 2021). The recoveries further validate the potential processability of the 3Ts mineralized material across new veins and at depth.

The table below shows recoveries for the three-stage tests on each of the vein composites:

	Tommy Vein	Johnny Vein		
	Total Gold Recovery	Total Silver Recovery	Total Gold Recovery	Total Silver Recovery
Gravity, Floatation and Leach Testing	91.9%	91.5%	89.5%	85.8%

"We are pleased to receive the latest results from the metallurgical testing," stated Randy Turner, President and CEO of Independence Gold. "These results give further confidence in previous recoveries conducted

using vein material collected from the untested Larry and Johnny veins, as well as a Tommy vein sample that was taken at a significant depth. These results strengthen the viability of the 3Ts Project to support future resource growth and potential economic development."

Wildfire Update

Wildfire G41658 continues to burn out of control, with an evacuation order still in place affecting the 3Ts Project camp. This wildfire has grown to more than 2,100 hectares in size, with crews and heavy equipment creating fire breaks around the camp; structure protection is currently in place taking steps to protect both the camp and the two core storage areas.

About Independence

Independence Gold Corp. is a well-financed mineral exploration company with holdings ranging from early-stage grassroots exploration to advanced-stage resource expansion in British Columbia and Yukon. The Company is positioned to add shareholder value through systematic project advancement, while management continues to evaluate additional gold and silver projects for possible acquisition. For additional information, visit the Company's website www.ingold.ca.

Andy Randell, P.Geo., the Company's Qualified Person as defined by National Instrument 43-101 and who is an independent consultant for the Company, has reviewed the technical information in this news release.

ON BEHALF OF THE BOARD OF INDEPENDENCE GOLD CORP.

"Randy Turner"

Randy Turner, President and CEO

Neither the TSX Venture Exchange nor its Regulation Services Provider (as that term is defined in policies of the TSX Venture Exchange) accepts responsibility for the adequacy or accuracy of this release.

Notes for Disclosure

- All recoveries are based on bench-scale tests at 80% passing 100 µm; gravity values refer to Mozley concentrate reporting from Knelson concentrate; leach extractions are 72-hr bottle rolls on gravity or final flotation tails, as applicable.
- Averages are program-level (three composites) and rounded to one decimal place for readability. Potential optimization steps (e.g., pre-oxidation, oxygen sparging, CN dosage) were identified for future work.

Methodology

Approximately 100 kg of crushed (3.35 mm) material from the 3Ts Project was delivered to Base Metallurgical Laboratories and combined into three master composites for testing. The program evaluated two conventional flowsheets at a primary grind of 80% passing 100 µm:

- gravity concentration followed by cyanide leaching of the gravity tails; and
- gravity concentration, flotation of the gravity tails, then cyanide leaching of the final flotation tails.

Gravity concentration used a Knelson concentrator with Mozley upgrade to produce a gravity concentrate and a gravity tail for downstream testing. Flotation was performed in a 4.4 L Denver D12 mechanical cell with air, using PAX 407 collector and MIBC frother at a pH of approximately 8.5. Cyanidation tests on appropriate tails were conducted at 40% solids with NaCN maintained at 1 g/L and pH 10.5-11 under air sparging, with monitoring to 72 hours.

For this testing the gravity concentrate, and flotation concentrate were assumed to be 100% extracted. Therefore, the overall extraction is based on a 100% assumed extraction for this stream.

Testing Results Per Stage

The following section shows results for composites during each stage of testing. The full metallurgical report

will be available on the Independence Gold website.

Head Results:

The following table summarizes the assays results for both composite samples:

Sample	Assays	
	Au g/t	Ag g/t
Tommy Vein "Deep"	2.89	26.00
Johnny Vein	4.85	56.00
Larry Vein	4.75	91.00

Gravity Separation:

A stand-alone gravity step recovered a meaningful portion from each master composite. Gold and silver reporting to the Mozley concentrate were:

- Composite 1 (Tommy Vein, Deep):
- Composite 2 (Johnny Vein System):
- Composite 3 (Larry Vein):

● 17
● 8.3
● 29

Across all three composites, the program-level average gravity recovery was 17.4% gold and 8.6% silver.

Gravity and Leaching Tests:

Cyanidation leaching of the gravity tails was performed over a 72-hour process, which led to an overall increase in recoveries:

- Composite 1 (Tommy Vein, Deep):
- Composite 2 (Johnny Vein System):
- Composite 3 (Larry Vein):

● 89
● 86
● 96

	Tommy Vein		Johnny Vein	
	Total Gold Recovery	Total Silver Recovery	Total Gold Recovery	Total Silver Recovery
Gravity Testing Only	14.9%	7.9%	8.3%	4.4%
Gravity & Leach Testing	89.2%	77.1%	86.6%	75.3%
Gravity, Floatation and Leach Testing	91.9%	91.5%	89.5%	85.8%

Drill Hole Information from this release

Drill Hole	Easting	Northing	Elevation	Azimuth*	Dip	Total	Meterage
3TS-24-27 363859 5876772 1182	270	62	451				
3TS-25-05 363044 5876910 1214	90	90	276				
3TS-25-07 363940 5876982 1150	270	70	330				

* All drill hole locations are in NAD83, Zone 10 Datum

**Based on true north. For magnetic declination add 17.5 degrees

All statements in this press release, other than statements of historical fact, are "forward-looking information" with respect to Independence within the meaning of applicable securities laws, including statements with respect to the Company's planned drilling and exploration activities. The Company provides forward-looking statements for the purpose of conveying information about current expectations and plans relating to the future and readers are cautioned that such statements may not be appropriate for other purposes. By its nature, this information is subject to inherent risks and uncertainties that may be general or specific and which give rise to the possibility that expectations, forecasts, predictions, projections or conclusions will not prove to be accurate, that assumptions may not be correct and that objectives, strategic goals and priorities will not be achieved. These risks and uncertainties include but are not limited to those identified and reported in Independence's public filings under Independence Gold Corp.'s SEDAR profile at www.sedarplus.ca. Although Independence has attempted to identify important factors that could cause actual actions, events or results to differ materially from those described in forward-looking information, there may be other factors

that cause actions, events or results not to be as anticipated, estimated or intended. There can be no assurance that such information will prove to be accurate as actual results and future events could differ materially from those anticipated in such statements. Independence disclaims any intention or obligation to update or revise any forward-looking information, whether as a result of new information, future events or otherwise unless required by law.

Suite 580 - 625 Howe Street, Vancouver, British Columbia V6C 2T6

Telephone: 604-687-3959

Faxsimile: 604-687-1448

E-Mail: info@ingold.ca

To view the source version of this press release, please visit <https://www.newsfilecorp.com/release/265797>

Dieser Artikel stammt von [Rohstoff-Welt.de](https://www.rohstoff-welt.de)

Die URL für diesen Artikel lautet:

<https://www.rohstoff-welt.de/news/704620--Independence-Gold-Reports-Metallurgy-Results-from-the-3Ts-Project-BC.html>

Für den Inhalt des Beitrages ist allein der Autor verantwortlich bzw. die aufgeführte Quelle. Bild- oder Filmrechte liegen beim Autor/Quelle bzw. bei der vom ihm benannten Quelle. Bei Übersetzungen können Fehler nicht ausgeschlossen werden. Der vertretene Standpunkt eines Autors spiegelt generell nicht die Meinung des Webseiten-Betreibers wieder. Mittels der Veröffentlichung will dieser lediglich ein pluralistisches Meinungsbild darstellen. Direkte oder indirekte Aussagen in einem Beitrag stellen keinerlei Aufforderung zum Kauf-/Verkauf von Wertpapieren dar. Wir wehren uns gegen jede Form von Hass, Diskriminierung und Verletzung der Menschenwürde. Beachten Sie bitte auch unsere [AGB/Disclaimer](#)!

Die Reproduktion, Modifikation oder Verwendung der Inhalte ganz oder teilweise ohne schriftliche Genehmigung ist untersagt!

Alle Angaben ohne Gewähr! Copyright © by Rohstoff-Welt.de -1999-2026. Es gelten unsere [AGB](#) und [Datenschutzrichtlinen](#).